



versalis

info.styrenics@versalis.eni.com

Technical Data Sheet

Edistir® RK 451G

Polystyrene

UL94 V-0, polybromobiphenylether (PBBE) free, flame retarded, high impact polystyrene.
This grade combines medium flow, heat resistance and good light stability for injection moulding of technical parts.
Designation: Thermoplastics ISO 2897-PS-I, MF, 088-06-04-18

Applications

Printers and copiers, ventilators, TV back covers, business machines, monitor cabinets.

Typical processing data

- Injection moulding:
predrying recommended at 70°C for 2 h
- melt temperature 190-230°C
 - mould temperature 20-60°C

General information

RK 451G can be supplied in a natural or coloured version upon request.
This grade is certified UL94 V-0 at 1.5 mm "all colors";
UL94-5VA at 6.0 mm "all colors" in the foamed version at density from 0.86 to 1.2 g/cm³ and
UL94-5VA at 4.0 mm "all colors" in the foamed version at density from 0.96 to 1.2 g/cm³ (UL file E83071).

Property	Test Conditions	Test method	Units	Values
General				
Water absorption	24h - 23°C	ISO 62	%	<0,1
Density	-	ISO 1183	g/cm ³	1,15
Bulk density	-	ISO 60	g/cm ³	0,7
Rheological				
Melt flow rate	200°C - 5kg	ISO 1133	g/10'	4
Mechanical				
Tensile strain at break	50 mm/min	ISO 527	%	50
Tensile stress at break	50 mm/min	ISO 527	MPa	22
Tensile stress at yield	50 mm/min	ISO 527	MPa	23
Flexural strength	2 mm/min	ISO 178	MPa	31
Tensile modulus	1 mm/min	ISO 527	MPa	1650
Izod impact strength, notched	+23°C - 3,2mm	ISO 180/4A	J/m	80
Izod impact strength, notched	+23°C - 4mm	ISO 180/1A	kJ/m ²	6
Thermal				
Coefficient of linear thermal expansion	-	ASTM D 696	10 ⁻⁵ /°C	9
Thermal conductivity	-	ISO 8302	W/(K.m)	0,17
Moulding shrinkage	-	ISO 294/4	%	0,4 - 0,7
Deflection temperature under load (annealed)	1,82 MPa - 120°C/h	ASTM D 648	°C	85
Vicat softening temperature	50 N - 50°C/h	ISO 306/B	°C	90
Vicat softening temperature	10 N - 50°C/h	ISO 306/A	°C	98
Flammability				
Flame behaviour	1,5 mm	UL 94	cl.	V0
Glow wire test (GWT)	1,6 mm	IEC 60695-2-1	°C	850
Electrical				
Dielectric constant (relative permittivity)	50 Hz	IEC 60250	-	2,5
Dissipation factor	50 Hz	IEC 60250	-	0,0003
Comparative tracking index (CTI)	Sol. A	IEC 60112	-	400
Surface resistivity	-	IEC 60093	10 ¹⁵ ohm	>1,5
Volume resistivity	-	IEC 60093	10 ¹⁵ ohm.cm	>7
Dielectric strength	-	IEC 60243	kV/mm	26

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted.

Versalis is available to provide the guaranteed values for each product on demand.